



Die Zukunft des nachhaltigen und feuerbeständigen Bauens

Zertifizierung und Sicherheit

Luftschalldämmung MAGOXX 9mm

SHIN170300781CCM

info@magoxx.com

+31 (0) 88 3748400

www.magoxx.de



TEST REPORT

No. : SHIN170300781CCM

Date : Mar. 28, 2017

Page: 1 of 4

CUSTOMER NAME: SINH BUILDING SOLUTIONS B.V.

ADDRESS: OOSTEINDE 26, 2271 EH, VOORBURG, THE NETHERLANDS

Sample Name : SINH™ BOARD

Specification : thickness:9mm

Above information and sample(s) was/were submitted and confirmed by the client SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

Test Required : Airborne sound transmission loss

Test Method : ASTM E90-09

SGS Ref No. : IN-SH-CP-5612-17019

Date of Receipt : Mar. 22, 2017

Testing Start Date : Mar. 22, 2017

Testing End Date : Mar. 24, 2017

Test result(s) : For further details, please refer to the following page(s)
(Unless otherwise stated the results shown in this test report refer to the sample(s) tested)

Signed for
SGS-CSTC Standards Technical
Services Shanghai Co., Ltd.

Erin Huang
Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing inspection report & certificate, please contact us at telephone: (86-21) 61196300 1443, or email: CN.Doccheck@sgs.com

No.69, Block 1159, East Kang Qiao Road, Pudong District, Shanghai, China, 201319 (86-21) 61196300 (86-21) 61191853 (86-21) 61183620 www.sgs.com.cn
中国·上海·浦东康桥东路1159弄69号 邮编:201319 (86-21) 61196300 (86-21) 61191853 (86-21) 61183620 sgs.china@sgs.com

Member of the SGS Group (SGS SA)



TEST REPORT

No. : SHIN170 300781CCM

Date: Mar. 28, 2017

Page: 2 of 4

1. Test reference

- 1) ASTM E90-09 Standard test method for laboratory measurement of airborne sound transmission loss of building partitions and elements
- 2) ASTM E413-10 Classification for rating sound insulation

2. Sample detail

Dimension/Density	3000mmx1200mmx9mm/10.7kg/m ²
-------------------	---

3. Test condition

Air temperature in the test room	19.3	Air humidity in the test room	33.6%
Source room volume	125m ³	Receiving room volume	100m ³
Description of test arrangement	Area of test samples S is 10 m ²		

4. Test result

Rating according to ASTM E413-10:

Sound transmission class: STC 28dB

R_w(C;C_{tr})=28(-1;-3); R_w+C=27dB; R_w+C_{tr}=25dB

Clients requirement: STC>25dB

Conclusion: Pass

***** To be continued*****



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-use-Electronic.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.69, Block 1158, East Kang Qiao Road, Pudong District, Shanghai, China, 201319 t:(86-21)61196300 f:(86-21)61191853/98183620 www.sgs.com.cn
中国·上海·浦东康桥东路1159弄69号 邮编:201319 t:(86-21)61196300 f:(86-21)61191853/98183620 e: sgs.china@sgs.com

Member of the SGS Group (SGS SA)




TEST REPORT

No. : SHIN170 300781CCM

Date : Mar. 28, 2017

Page: 3 of 4

Frequency f Hz	Value(dB)
100	16.2
125	18.5
160	17.3
200	17.5
250	20.8
315	20.9
400	22.9
500	24.1
630	26.6
800	28.0
1000	28.5
1250	31.4
1600	31.8
2000	31.5
2500	30.0
3150	24.3
4000	30.4



Remark:

----- Frequency range according to ASTM E413-10

————— Curve of STC reference values according to ASTM E413-10

***** To be continued*****



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.69, Block 1159, East Kang Qiao Road, Pudong District, Shanghai, China, 201319 t:(86-21)61196300 f:(86-21)61191853/98183620 www.sgs.com.cn
中国·上海·浦东康桥东路1159弄69号 邮编:201319 t:(86-21)61196300 f:(86-21)61191853/98183620 e: sgs.china@sgs.com

Member of the SGS Group (SGS SA)




TEST REPORT

No. : SHIN170300781CCM

Date : Mar. 28, 2017

Page: 4 of 4

Structure:



Note: The test was carried out by external laboratory assessed as competent.

***** End of report*****



SGS Group (SGS SA)
Testing Center Construction Materials Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.69, Block 1159, East Kang Qiao Road, Pudong District, Shanghai, China, 201319 t:(86-21) 61196300 f:(86-21) 61191853/98183620 www.sgs.com.cn
中国·上海·浦东康桥东路1159弄69号 邮编:201319 t:(86-21) 61196300 f:(86-21) 61191853/98183620 e: sgs.china@sgs.com

Member of the SGS Group (SGS SA)

MAGOXX®

Die Zukunft des nachhaltigen und feuerbeständigen Bauens

MAGOXX B.V.
Caballero Fabrik
Saturnusstraat 60, Einheit 71
2516 AH Den Haag
(Niederlande)
+31 (0) 88 3748400